

TMF-150

Medium Elongation, Multilayer Nylon Bagging Film

Features:

- Tough multilayer nylon based vacuum bagging film.
- Designed for processing advanced composite structures.
Ideal for use for both resin infusion and prepreg molding applications.
- Maximum recommended temperature use of 300°F (149°C).
- Not suited for autoclave processing.

Properties:

Technical Data:	Test Method:	Typical Value:
Max. use temperature		300°F (149°C)
Color		Blue
Tensile Strength	ASTM D-882	>6,200 psi
Elongation (at break)	ASTM D-882	>380%

The above values are "Typical Values" which have a nominal range about them and are not intended for specification purposes.

Availability:

- Standard Format: Sheet, V-Sheet & Lay-Flat Tubing
Roll Widths: up to 470"
Film Gauge: .0025" and .003"
Roll Length: up to 500'

Storage:

- Store in original packaging and protect from the environment. Do not store vertically on end.

Health & Safety:

- Handling of these products must conform to individual company guidelines and health and safety regulations.

Technology Marketing, Inc.

P: 801.265.0111 • F: 801.265.0184

6122 Stratler Street • Salt Lake City, UT 84107 USA • customerservice@tmi-slc.com • www.tmi-slc.com

ISO 9001:2015 & AS9120B Certified

Note: Data provided is for information only and does not constitute any warranty for the product as the conditions and varying methods of use are beyond our control. Technology Marketing Inc. shall not be liable for any special indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use or inability to use these materials. These materials are provided "as is" without warranty of any kind, either expressed or implied including, but not limited to the implied warranties of merchantability or fitness for a particular purpose