



HexForce™ 4579

Fiber Glass Fabric

Product Data

STYLE 4579		US System	SI Units
Type of Yarns	Warp Yarn:	SCG 150 1/2	SC9 34x2
	Fill Yarn:	SCG 75 1/0	SC9 68
Fabric Weight, Dry		3.59 oz/yd ²	122 g/m ²
Weave Style	Plain		
CONSTRUCTION			
Nominal Construction	Warp Count:	30/in	11.81/cm
	Fill Count:	16/in	6.29/cm
Fabric Thickness		5.40 mil	0.14 mm
Breaking Strength	Warp	300 lbf/in	
	Filling	300 lbf/in	

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



1913 North King Street
Seguin, Texas 78155
Phone: 830-379-1580
Fax: 830-379-9544
Customer Service Toll Free: 1-866-601-5430

For European sales office numbers and a full address list, please go to:
<http://www.hexcel.com/contact/salesoffices>