

# TMF-350

## *High Elongation, High Temperature Bagging Film*

### Features:

- Clear copolymer bagging film with high elongation and high temperature stability.
- Designed for prolonged cures to 350°F (176°C) and remains soft and pliable.
- Ideal suited for highly contoured parts, tight corners, and pressurized bladders, where softness and high elongation are crucial.
- Engineered for use with 350°F (176°C) curing epoxy resin systems.
- Not suited for use with polyester and vinyl-ester resins.

### Properties:

Technical Data:	Test Method:	Typical Value:
Maximum use temperature		350°F (176°C)
Color		Clear
Tensile Strength	ASTM D-882	9,800 psi
Elongation (at break)	ASTM D-882	450%

The above values are "Typical Values" which have a nominal range about them and are not intended for specification purposes.

### Availability:

- Standard Format: 60" x .003" x 1000' Sheeting  
60" x .003" x 500' V-Sheeting (Opens to 120")
- (Other configurations may be available upon request. Minimums may apply.)

### Storage:

- Store in original packaging and protect from the environment. Do not store vertically on end.

### Health & Safety:

- Handling of these products must conform to individual company guidelines and health and safety regulations.

***Technology Marketing, Inc.***

P: 801.265.0111 • F: 801.265.0184

6122 Stratler Street • Salt Lake City, UT 84107 USA • [customerservice@tmi-slc.com](mailto:customerservice@tmi-slc.com) • [www.tmi-slc.com](http://www.tmi-slc.com)

**ISO 9001:2015 & AS9120B Certified**

Note: Data provided is for information only and does not constitute any warranty for the product as the conditions and varying methods of use are beyond our control. Technology Marketing Inc. shall not be liable for any special indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use or inability to use these materials. These materials are provided "as is" without warranty of any kind, either expressed or implied including, but not limited to the implied warranties of merchantability or fitness for a particular purpose