

TMR-4760

Modified Polymer Release Film

Features:

- Modified polymer release film, offers a durable release for applications up to 400°F (205°C).
- Excellent release from epoxy, phenolic, and other resin systems.
- Provides an inexpensive alternative to higher temperature, higher elongation release films.
- Suited for application with parts that have flat or mild contours

Properties:

Technical Data:	Test Method:	Typical Value:
Maximum use temperature		400°F (204°C)
Color		Blue, Clear
Tensile Strength (at break)	ASTM D-882	> 4,400 PSI
Elongation (at break)	ASTM D-882	> 300%
Yield		228ft ² /lb/mil

The above values are "Typical Values" which have a nominal range about them and are not intended for specification purposes.

Availability:

- Standard roll sizes: 54" x .002" x 1,500'
60" x .002" x 1,800'
- Perforation: Please call for availability.

Storage:

- Store in original packaging and protect from the environment.

Health & Safety:

- Handling of these products must conform to individual company guidelines and health and safety regulations.

Technology Marketing, Inc.

P: 801.265.0111 • F: 801.265.0184

6122 Stratler Street • Salt Lake City, UT 84107 USA • customerservice@tmi-slc.com • www.tmi-slc.com

ISO 9001:2015 & AS9120B Certified

Note: Data provided is for information only and does not constitute any warranty for the product as the conditions and varying methods of use are beyond our control. Technology Marketing Inc. shall not be liable for any special indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use or inability to use these materials. These materials are provided "as is" without warranty of any kind, either expressed or implied including, but not limited to the implied warranties of merchantability or fitness for a particular purpose