

VALUE PLY™

VP 102

Style: 56228

Polyester Peel/Release Ply

VP 102, Style 56228 is designed for vacuum bag lay-up composites and metal-to-metal bonding structures. The 100% polyester fiber melts at approximately 480°F (249°C) and is resistant to phenolic resin system degradation. The fabric leaves a **rough** surface impression for priming and secondary bonding. It is available in precision slit widths of 58 inches or less. **This fabric contains blue identification yarns for easy visibility.**

Style 56228 is available in:
FIN 070 – SWF – Proprietary

<u>Physical Properties</u>	<u>US</u>	<u>Metric</u>	<u>Test Method</u>
Width	60 in	152.4 cm	ASTM-D-3774
Length	300 yd	274.3 m	
Weight	2.70 oz/yd ²	91.5 g/m ²	ASTM-D-3776
Finished Count			ASTM-D-3775
Warp	40 ends/in	15.7 ends/cm	
Fill	43 picks/in	16.9 picks/cm	
Thickness	0.006 in	0.15 mm	ASTM-D-1777
Tensile Strength (Grab)			ASTM-D-5034
Warp	160 lb min	712 N	
Fill	180 lb min	801 N	

The data above represents typical values for this fabric. A specification for this product has not yet been established.

For More Information, Please Contact Us:

Precision Fabrics Group, Inc.
 301 North Elm Street, Suite 600
 Greensboro, NC 27401
www.precisionfabrics.com

JKH 11/01/06