



# HexForce™ 2313

Fiber Glass Fabric

## Product Data

STYLE 2313		US System	SI Units
<b>Type of Yarns</b>	<b>Warp Yarn:</b>	ECE 225 1/0	EC7 22
	<b>Fill Yarn:</b>	ECD 450 1/0	EC5 11
<b>Fabric Weight, Dry</b>		2.40 oz/yd <sup>2</sup>	81 g/m <sup>2</sup>
<b>Weave Style</b>	Plain		
<b>CONSTRUCTION</b>			
<b>Nominal Construction</b>	<b>Warp Count:</b>	60/in	23.62/cm
	<b>Fill Count:</b>	64/in	25.19/cm
<b>Fabric Thickness</b>		3.0 mil	0.08 mm
<b>Breaking Strength</b>	<b>Warp</b>	220 lbf/in	
	<b>Filling</b>	120 lbf/in	

### IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory and minimum order quantities may apply.

### FOR FURTHER INFORMATION, PLEASE CONTACT US



1913 North King Street  
Seguin, Texas 78155  
Phone: 830-379-1580  
Fax: 830-379-9544  
Customer Service Toll Free: 1-866-601-5430

For European sales office numbers and a full address list, please go to:  
<http://www.hexcel.com/contact/salesoffices>