

# QUICK DRAW™ (PA-6000)

## *Self-Venting High Temperature Embossed Nylon 6 Bagging Film*

### Features:

- Self-venting, high temperature, embossed texture, Nylon 6 bagging film.
- Designed to eliminate the need for breathers and release film in general vacuum bagging processes.
- Ideal for vacuum bagging de-bulk or compaction cycles for prepregs, wet lay ups, UV cured resins, resin infusion, without using breather/bleeders, flow media, and release films.
- Embossed texture provides rapid, controlled evacuation of little or no air/volatile entrapment.
- Capable of withstanding temperatures up to 400°F (205°C).

### Properties:

Technical Data:	Test Method:	Typical Value:
Max. use temperature		400°F (205°C)
Color		Green
Shrinkage @ 350°F (117°C)		>5%
Flammability		Self-Extinguishing
Tensile Strength	ASTM D-882	15,000psi
Yield Strength	ASTM D-882	4,600psi
Elongation (at break)	ASTM D-882	425%

The above values are "Typical Values" which have a nominal range about them and are not intended for specification purposes. (Quick Draw™ is a trade mark of Film Technology, Inc. U.S. Patent No. 5129813)

### Availability:

- Standard Format: Sheeting on 3" or 6" cores
- Roll Widths: up to 140"
- Standard Thickness: .002" & .003" (Gauge Control +/- 10%)

### Storage:

- Store in original packaging and protect from the environment. Do not store vertically on end.

### Health & Safety:

- Handling of these products must conform to individual company guidelines and health and safety regulations.
- Quick Draw™ (PA-6000) can be damaged by contact with the following chemicals: M Cresol, Formic Acid, Phenol, Potassium Thiocyanate, and 2,2,3,3, Tetra Fluor propane.

**Technology Marketing, Inc.**

P: 801.265.0111 • F: 801.265.0184

6122 Stratler Street • Salt Lake City, UT 84107 USA • [customerservice@tmi-slc.com](mailto:customerservice@tmi-slc.com) • [www.tmi-slc.com](http://www.tmi-slc.com)

**ISO 9001:2015 & AS9120B Certified**

Note: Data provided is for information only and does not constitute any warranty for the product as the conditions and varying methods of use are beyond our control. Technology Marketing Inc. shall not be liable for any special indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use or inability to use these materials. These materials are provided "as is" without warranty of any kind, either expressed or implied including, but not limited to the implied warranties of merchantability or fitness for a particular purpose