

VALUE PLY™

VP 200

Style: 66416

Nylon Peel/Release Ply

VP 200, Style 66416 is designed for vacuum bag lay-up composites and metal-to-metal bonding structures. The 100% nylon fiber melts at approximately 480°F (249°C). The fabric is not recommended for phenolic systems. The fabric leaves a **fine** surface impression for priming and secondary bonding. It is available in precision slit widths of 58 inches or less.

Style 66416 is available in:

FIN 060 – NAT – Scoured and Heat-Set finish

FIN 068 – SRL – Super Release Lavender™/an inert, heat stabilized, cross-linked polymer finish

<u>Physical Properties</u>	<u>US</u>	<u>Metric</u>	<u>Test Method</u>
Width	60 in	152.4 cm	ASTM-D-3774
Length	300 yd	274.3 m	
Weight	1.75 oz/yd ²	59.3 g/m ²	ASTM-D-3776
Finished Count			ASTM-D-3775
Warp	154 ends/in	60.6 ends/cm	
Fill	96 picks/in	37.8 picks/cm	
Thickness	0.005 in	0.127 mm	ASTM-D-1777
Tensile Strength (Grab)			ASTM-D-5034
Warp	100 lb min	445 N	
Fill	120 lb min	534 N	
pH	4.0 – 8.0		AATCC-81
Extractable Materials	0.5% max		ASTM-D-2257 Petroleum Ether Method

The data above represents typical values for this fabric. A specification for this product has not yet been established.

For More Information, Please Contact Us:

Precision Fabrics Group, Inc.

301 North Elm Street, Suite 600

Greensboro, NC 27401

www.precisionfabrics.com

JKH 11/01/06